

**KANSAS DEPARTMENT OF TRANSPORTATION  
 SPECIAL PROVISION TO THE  
 STANDARD SPECIFICATIONS, EDITION 2007**

**SECTION 1107**

**AGGREGATES FOR BACKFILL**

**Page 1100-20, subsection 1107.2. Delete TABLE 1107-1: AGGREGATES FOR STRUCTURES OR PIPE BACKFILL and associated bullets and replace with the following:**

<b>TABLE 1107-1: AGGREGATES FOR STRUCTURES OR PIPE BACKFILL</b>										
Type	% Retained-Square Mesh Sieves									Plasticity Index (Max.)
	2"	1 1/2"	1"	3/4"	3/8"	No. 4	No. 8	No. 40	No. 200	
SB-1	0	0-10		15-40	50-75		95-100			
SB-2			0	0-20	40-70	75-100	95-100			
SB-3	0	0-5		5-30		35-60	45-70	60-84	80-92	1-8
PB-1 <sup>1</sup>	0	0-10		15-40	50-75		95-100			
PB-2 <sup>1</sup>			0	0-20	40-70	75-100	95-100			
PB-3 <sup>1</sup>			0	0-30		35-60	50-75	70-90	90-100	8

<sup>1</sup>Use of PB is required for PE and PVC pipe backfill.

**Page 1100-20, subsection 1107.2a.(3)(b). Delete this subsection and replace with the following:**

- (b) Deleterious Substances.
  - Shale or shale-like material, maximum (KT-8) ..... 3.0%
  - Clay Lumps and friable particles, maximum (KT-7) ..... 3.0%
  - Sticks (wet), maximum (KT-35) ..... 1.0%

**Page 1100-20, subsection 1107.2a. Add a new section (4) as follows:**

(4) Foundation Stabilization. Use SB aggregates at those locations where the use of SB aggregates for foundation stabilization is specified elsewhere in the Contract Documents. When the preceding sentence applies, use SB-3 when the expected depth of foundation stabilization is less than 6 inches.

Except at the locations described above, the use of alternate granular materials (except chat) may be permitted, but only with the approval of the District Materials Engineer.

**Page 1100-20, subsection 1107.2b. Delete this subsection and replace with the following:**

**b. MSE Walls:** Precast Panel and Modular Block with Steel Soil Reinforcing Mesh or Steel Reinforcing Strips and Tie Strips.

(1) Composition. Use granular backfill material in the structure volume of sand, sand-gravel, or crushed stone, reasonably free from organics or other deleterious materials, and complies with the following:

(2) Quality. Submit representative material samples for the following tests to the Materials and Research Center, 2300 Van Buren, Topeka, KS 66611 (ATTENTION: Geotechnical Engineer) for acceptance prior to utilizing this material on the project.

(a) The Plasticity Index (P.I.) is 6 maximum, determined by KT-10.

(b) An angle of internal friction of 34 degrees or greater, as determined by the standard direct shear test – AASHTO T 236, utilizing a sample of the material compacted to 95 percent of

AASHTO T 99 Methods C or D (with oversize correction, as outlined in Note 9 in AASHTO T 99) at optimum moisture content.

(c) Soundness. Use material substantially free of shale or other soft, poor durability particles as determined in accordance with **SECTION 1115**. “Freeze and Thaw”, minimum 0.90 as determined in **DIVISION 1100**. Los Angeles Wear Abrasion, maximum 40%.

(d) Provide material that complies with **TABLE 1107-2**.

<b>TABLE 1107-2: ELECTROCHEMICAL REQUIREMENTS (PANEL)</b>	
<b>Requirements</b>	<b>Test Method</b>
Resistivity > 5000 ohm-cm	AASHTO T 288
pH: 5.0 to 10.0	AASHTO T 289
Organic Content < 1%	AASHTO T 267

If the resistivity is less than 5000 ohm-cm, but greater than 3000 ohm-cm, the backfill material can be accepted if it complies with **TABLE 1107-3**.

<b>TABLE 1107-3: ADDITIONAL ELECTROCHEMICAL REQUIREMENTS</b>		
<b>Property</b>	<b>Requirements</b>	<b>Test Method</b>
Chlorides	< 100 parts per million	ASTM D 4327
Sulfates	< 200 parts per million	ASTM D 4327

(3) Product Control.

(a) Gradation.

<b>TABLE 1107-4: AGGREGATES FOR PANEL MSE WALLS BACKFILL</b>			
<b>Sieve Size</b>	<b>4"</b>	<b>No. 40</b>	<b>No. 200</b>
<b>Percent Retained</b>	<b>0</b>	<b>40 - 100</b>	<b>95 - 100</b>

(b) Coefficient of Uniformity. Provide material with a minimum coefficient of uniformity of 4.0 as defined by ASTM D 2487 for systems that utilize steel reinforcing strips and tie strips (Reinforced Earth). Material with a coefficient of uniformity less than 4.0 may be accepted based on the results of pullout tests conducted by the University of Kansas, Civil Engineering Department, Geotechnical Section. (Contact: Dr. Jie Han @ 785-864-3714 or Dr. Bob Parsons @ 785-864-2946.)

(4) Use only crushed stone in District 1.

For select granular backfill material composed of crushed stone, submit a proposed project gradation with single-point gradations and tolerances for approval. For sand and sand-gravel combinations, a project gradation will be issued that will specify gradation tolerances after the proposed material is approved. Any quality assurance samples which fall outside the tolerances will necessitate re-approval to be in compliance with **subsection 1107.2 b.(2)**.

**Page 1100-21, subsection 1107.2c. Delete this subsection and replace with the following:**

**c. MSE Walls: Modular Block with Soil Reinforcing Geogrid.**

(1) Composition. Use granular backfill material in the structure volume of sand, sand-gravel, or crushed stone, reasonably free from organics or otherwise deleterious materials, and complies with the following:

(2) Quality. Submit representative material samples for the following tests to the Materials and Research Center, 2300 Van Buren, Topeka, KS 66611 (ATTENTION: Geotechnical Engineer) for acceptance prior to utilizing this material on the project.

(a) The Plasticity Index (P.I.) is 6 maximum, determined by KT-10.

(b) An angle of internal friction of 34 degrees or greater, as determined by the standard direct shear test – AASHTO T 236, utilizing a sample of the material compacted to 95% of AASHTO

T 99 Methods C or D (with oversize correction, as outlined in Note 9 in AASHTO T 99) at optimum moisture content.

(c) Soundness. "Freeze and Thaw", minimum 0.90 as determined in **DIVISION 1100**. Los Angeles Wear Abrasion, maximum 40%.

(d) Provide material that complies with **TABLE 1107-5**.

<b>TABLE 1107-5: ELECTROCHEMICAL REQUIREMENTS (Block)</b>		
	<b>Requirements</b>	<b>Test Method</b>
(Mesa)	pH > 3.0	AASHTO T 289
(Anchor Landmark)	pH: 3.0 to 9.0	AASHTO T 289
	Organic Content < 1%	AASHTO T 267

(3) Product Control.

(a) Gradation.

<b>TABLE 1107-6: AGGREGATES FOR MODULAR BLOCK MSE WALLS BACKFILL</b>			
<b>Type of Material</b>	<b>% Retained – Square Mesh Sieves</b>		
	<b>1"</b>	<b>No. 40</b>	<b>No. 200</b>
Sand	0	40-100	95-100
Crushed Stone	0	40-100	95-100

Limit the maximum particle size to ¾ inch for geosynthetic reinforced structures and for epoxy or PVC coated reinforcements. Use only crushed stone in District 1.

For select granular backfill material composed of crushed stone, submit a proposed project gradation with single-point gradations and tolerances for approval. For sand and sand-gravel combinations, a project gradation will be issued that will specify gradation tolerances after the proposed material is approved. Any quality assurance samples which fall outside the tolerances will necessitate re-approval to be in compliance with **subsection 1107.2 c.(2)**.

**Page 1100-22, subsection 1107.2d.(1). Delete this subsection and replace with the following:**

(1) Composition. Provide washed aggregate Type BD-1 and Type UD-1 composed of crushed or uncrushed gravel, or crushed stone.