KANSAS DEPARTMENT OF TRANSPORTATION SPECIAL PROVISION TO THE STANDARD SPECIFICATIONS, EDITION 2015

SECTION 1732

GEOFOAM

1732.1 DESCRIPTION

This specification covers the geofoam lightweight Expanded Polystyrene (EPS) fill for use at locations as designated in the Contract Documents. This includes lightweight embankment fill and to fill formed voids in the embankment behind abutments.

1732.2 MATERIALS

a. General. Use EPS blocks in standard sizes that are typically from 4 feet wide x 2.5 feet thick x 8 to 16 feet long.

Treat all EPS blocks with a tested and proven EPA registered material complying with ICC ES EG239 for termite treatment with a minimum 3 year field exposure limit.

Provide a minimum of 4 Geogripper Plates per block to restrain the EPS from moving laterally in layer over layer applications. Make the plate of galvanized or stainless steel with two-sided multi-barbed design capable of piercing the EPS. Make each plate capable of holding a lateral load of 60 lbs.

Use Grade 2.5 concrete for the cap that complies with the **SECTION 401**.

b. Fill. Provide EPS22 (or higher) type blocks complying with ASTM D 6817 with the minimum requirements shown in **TABLE 1732-1**:

TABLE 1732-1: EPS22 MINIMUM REQUIREMENTS		
Property	Requirement	
Density	1.35 lb/cu ft;	
Compressive Resistance	7.3 psi at 1% deformation	
Flexural Strength	35 psi	

c. Void Fill. Provide EPS12 type blocks complying with ASTM D 6817 with the minimum requirements shown in **TABLE 1732-2**.

TABLE 1732-2: EPS12 MINIMUM REQUIREMENTS		
Property	Requirement	
Density	0.70 lb/cu ft;	
Compressive Resistance	2.2 psi at 1% deformation	
Flexural Strength	10 psi	

1732.3 TEST METHODS

Test in accordance with ASTM D 6817.

1732.4 PREQUALIFICATION

Geofoam must be prequalified. Submit a written request to be evaluated for prequalification to the Bureau Chief of Construction and Materials. Provide the following for each brand and type of material to be evaluated:

- Name and address of the manufacturer.
- Brand name of the material.

• Two copies of a certified test report showing test results complying with the requirements of ASTM D 6817. Test results are to be no more than 36 months out of date.

1732.5 BASIS OF ACCEPTANCE

- a. Receipt and approval of a Type C certification as specified in DIVISION 2600.
- **b. Verification Testing**. Perform random sampling and testing for compressive strength and density in accordance with **TABLE 1732-3**. Failure of the samples to meet the compressive strength or density specification will serve as a basis for rejection of the entire lot as well as the product's removal from prequalified status.

TABLE 1732-3: TESTING FREQUENCY		
Embankment Volume (cubic yards)	Number of EPS Blocks Sampled	
< 650	3	
650 – 1300	4	
> 1300	5	

 $10\mbox{-}12\mbox{-}15$ BSGS (JJB) / C&M (CFN) Feb-16 Letting